Technical Data



Performance you can trust

GLASSFLO MPT SPRAY **Mould Pre-treatment Spray**

Glassflo MPT Spray is a dry-film blank mould pre-treatment specially formulated to remove the need for manual swabbing of moulds during start-up, so giving consistent running conditions.

Glassflo MPT Spray can also be applied to blow moulds, bottom plates, neck rings and other related equipment.

Features

- Clean, air cured, dry coating requires no baking.
- Prevents adhesion of ware to moulds.
- Promotes excellent glass distribution.
- Cost efficient through reduced mould dope usage.
- Consistent quality through even film.

Directions for Use

- 1. Ensure surfaces are clean, dry and free from oil or grease.
- 2. Apply a thin, even coat from a distance of 15-20cm.
- 3. Touch dry in approximately 1 minute.
- 4. For best results allow to cure at room temperature for 2-4 hours.
- After use invert can and spray until nozzle is
- 6. Lightly burnish the applied film for an excellent finish to ware.

T +44 (0) 113 232 2600 F +44 (0) 113 232 2740 E customer-service@rocol.com www.rocol.com

ROCOL House, Swillington, Leeds LS26 8BS

Registered Company No. 559693 VAT No. 742 0531 67 Registered Office: Admiral House, St Leonard's Road, Windsor, Berkshire SL4 3BL ROCOL A division of TW Ltd











Technical Data



Performance you can trust

GLASSFLO MPT SPRAY

Appearance	Thin, grey/black film
Solid Lubricant	Graphite
Binder	Organic resin
Solvent	Non-chlorinated
Storage	Storage temperature should be kept below 50°C. Storage area should be out of direct sunlight 4 years shelf life
Pack Sizes – Part codes	400ml - 78871

Date: Aug-16

T +44 (0) 113 232 2600 F +44 (0) 113 232 2740

E customer-service@rocol.com

www.rocol.com

ROCOL House, Swillington, Leeds LS26 8BS

Registered Company No. 559693 VAT No. 742 0531 67 Registered Office: Admiral House, St Leonard's Road, Windsor, Berkshire SL4 3BL ROCOL A division of TW Ltd









